



CureCaulk 986

Tile and Fixture Caulk

PRODUCT DESCRIPTION

CURECAULK 986 is a superior quality siliconized acrylic latex caulk that is mold and mildew resistant. The product forms a long-lasting, flexible, water tight seal that will resist cracking on most building materials, including glass, wood, ceramic, metal and stone. CURECAULK 986 is available in all of C-Cure's grout colors.

BASIC USE

CURECAULK 986 fills joints between panels, cracks between walls and seals around tubs, showers, sinks and countertops, woodwork, baseboards, doors and window frames. CURECAULK 986 is an excellent adhesive for ceramic tile, glass, cork, wood, metal and acoustical tile, and is ideal for setting marble vanity tops to their bases.

LIMITATIONS

Do not apply when temperatures fall below 40°F (4°C). For interior use only.

PACKAGING

10.3 oz. (.29 kg) cartridge

APPLICABLE STANDARDS

Conforms to the requirements for elastomeric joint sealants, ASTM C920. Test in accordance with standard specifications, ASTM C-834.

INSTALLATION

SURFACE PREPARATION

Surface should be dry and clean, free of dust, loose paint, oil, grease and wax.

CONSTRUCTION/EXPANSION/ EXTERIOR CONTROL JOINTS/ ISOLATION JOINTS

Carry these types of joints through any subsequent finishing material. Clean the joint and install open or closed cell backer rod to the proper depth as outlined in EJ171 in the Tile Council Handbook.

APPLICATION

Insert cartridge into caulking gun. Cut off tip to desired size. Apply caulk in a smooth continuous bead and force into crack. CURECAULK 986 may be tooled with a dampened putty knife or caulking tool. Full cure is reached in 48 to 72 hours depending on the ambient temperature and humidity. When applied in areas exposed to moisture, wait at least 12 hours before using water. Unused portion of CURECAULK 986 should be capped and stored in a cool, dry place and used within one year.

CLEAN UP

Clean hands and tools with water. Clean up misapplied sealant with a damp cloth or sponge.

CAUTION

Do not take internally.
KEEP OUT OF REACH OF CHILDREN.

CURECAULK 986 TECHNICAL DATA

TEST	TYPICAL PROPERTIES
A. Base	Siliconized water based elastomeric acrylic.
B. Solvent	Water
C. Colors	Almost unlimited color range, which can be matched to tile, fixture, etc.
D. Solids	80%
E. Weight Per 10.5 oz.	1 lb. (.45 kg)
F. Application Temperature	40°F to 100°F (4°C to 38°C)
G. Consistency	Medium mastic
H. Open Time	10 to 20 Minutes
I. Set Time	48 Hours
J. Full Cure	14 Days
K. Clean Up	Soapy water is best, or water.
L. Flammability	None (wet state)
M. Freeze-Thaw State	Do not freeze.
N. Odor	Slight ammonia
O. Mildew Resistance	Good
P. Shelf Life	18 - 24 months when stored in original unopened container.
Q. Hardness	Shore A - 10
R. Elongation	115%
S. Tensile Strength	39 psi (3.1 kg/cm ²) min

GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-Cure and are given for informational purposes ONLY and without any responsibility for their use.

C-Cure MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-Cure specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall C-Cure be liable for incidental or consequential damages. C-Cure neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-Cure, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from the use of the product.

This writing constitutes a complete and exclusive statement of the understanding between C-Cure and buyer. There were no oral agreements or warranties, expressed or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-Cure.

Members of National Tile Contractors Association,

Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent. In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

C-CURE
Seal Beach, CA 90740
800-895-2874
www.c-cure.com