

Dry-Set Grout

PRODUCT DESCRIPTION

► BASIC USE

SUPREME 925 Dry-Set Grout is a chemically intensified Portland cement-based grout which possesses exceptional working qualities and permanent joint life. It is non-shrinking, non-toxic and odorless. SUPREME 925 inhibits fungus growth and contains an inhibitor to neutralize complex heavy metal salt stains common with some soft bisque ceramic tiles.

► AREAS OF USE

SUPREME 925 is used in any installation area, residential or commercial, where joint widths will not be in excess of 1/8" (3 mm). It is most commonly used with absorptive or semi-vitreous ceramic tile for both interior and exterior use. SUPREME 925, because of its very fine texture, is an excellent grout for use with highly glazed tiles to produce a smooth, dense joint. Only the addition of water is required. As an alternative to water, CUREMIX® 937, CURECRYLIC 938 or PROGROUT ADDITIVE 945 can be used to intensify its bond and flexural strength plus improve its color intensity and stain resistance for installations subject to exterior or severe use.

► LIMITATIONS

SUPREME 925, because of its Portland cement base, should not be used where high acid resistance is required. In areas of intermittent mild acid exposure, CUREMIX 937, CURECRYLIC 938 or PROGROUT ADDITIVE 945 used in lieu of water will improve its resistance to staining, thermal shock and acid. SUPREME 925 is not effected by prolonged contact with water, but does not form a waterproof barrier. The potential for efflorescence is inherent in all cement based products and is not considered a manufacturing defect.

► APPLICABLE STANDARDS

SUPREME 925 may be used in installations that must conform to ANSI 108.1, A108.4, A108.5, A108.7, A108.10 and ANSI A118.6 H2.3.

Color — SUPREME 925 is commonly available in white or gray. Colors are available in some areas.

Texture — Fine powder, consisting of Portland cement, organic and inorganic chemicals.

► PACKAGING

25 lb. (11.3 kg) bags, 5 lb. (2.27 kg) and 10 lb. (4.54 kg) containers.

INSTALLATION

► PREPARATORY WORK

Evaluation of the job conditions and the materials to be used will be the primary controlling factors that will determine the outcome of the job. As in all cases, if proper precautions are taken before a job is started, many problems that are within the realm of your control may be prevented, assuring a satisfactory job. The following is a suggested check list that one should follow to produce the best possible results when grouting a ceramic tile installation.

1) Wait a minimum of 48 hours before grouting a dry-set installation. Wait 72 hours before grouting a conventional mortar bed installation. Portland cement mortar beds that are excessively wet or have moisture coming through the slab may produce uneven drying conditions and efflorescence. Extra drying time is required to reduce the problem of efflorescence and uneven drying of the grout joint. If organic adhesives are used, a minimum of 48 hours is required for the evaporation of solvents which will prevent proper cure of the cement mortars. When epoxies are used, a minimum of 24 hours is required for the evaporation of solvents which will prevent proper cure of the cement mortars. These recommendations are made on the premise that the ambient temperature is 70°F (21°C), therefore, allowances should be made if the temperature is other than this. A longer time should be allowed for cooler temperatures and shorter times are possible if the temperature is higher.

2) The width and depth of all the joints should be uniform throughout the installation. If tile spacers or construction debris is present, it should be removed prior to grouting. A minimum of 2/3 of the joint shall be open for grouting material. Excessive setting material must be removed.

3) Plan your day's work so the next day's grouting does not join in conspicuous areas (*e.g. center of rooms*).

4) On exterior and interior work, it may be necessary to use shades or screens in work areas to prevent rapid water evaporation due to sun or wind. During warmer months, grouting should be done at the coolest part of the day. During cooler months, it will be necessary to protect the grout from freezing conditions for the first 72 hours.

5) If contrasting grout and tile colors are to be used, it may be necessary to use a grout release. It is best to check with the tile manufacturer for their recommendations or do a test panel simulating your job conditions.

6) Dampen the joints and wet the surface of the tile by means of fogging prior to placing the grout on the tile, however, no standing water should be present. This will

do three things: First, the grouting of a wet surface is easier. Second, it will reduce absorption of fine pigments and cement into the small pores of the tile, thus reducing cleanup time and possible staining. Third, this dampening of the joints will prevent the rapid loss of water from the grout, improving its color control and final hardness.

7) Keep grout from getting into the expansion joints, as it will later have to be cleaned out when sealant is applied.

8) During winter months, care should be taken that both the dry powder grout and mixing liquids are at least 60°F (16°C) and the grouted installation should be maintain at 60°F (16°C) or above for a minimum of 24 hours.

9) When grouting under adverse conditions such as below recommended temperatures or in highly humid conditions, mixing the grout with PROGROUT ADDITIVE 945 will decrease the chance of discoloration and help prevent efflorescence of the grout.

► MIXING

If possible, use the same person to mix the grout so that the same mixing technique will be used throughout the job. On small jobs, if less than a full bag is mixed at one time, the entire bag should be dry mixed first prior to the addition of water, CURECRYLIC 938 Admixture or PROGROUT ADDITIVE 945. This is done to prevent a color variance in the finished product that may be possible due to pigments and fine aggregates which have a tendency to settle while being transported. During the mixing process the grout should be mixed with as little liquid as is practical for application. The grout must be mixed thoroughly either by hand or with a low RPM power mixer to ensure uniform color and maximum strength. A suggested mixing procedure is as follows: To a mixing container, add approximately 3/4 gallon (2.84 L) of liquid per 25 lbs. (11.3 kg) of powder. Add the grout to the liquid using only a small amount of water to adjust consistency of the mortar. Allow the mortar to slake for 15 minutes, then remix. Do not retemper with liquid or powder after this point. Once the grout mortar has become too stiff to work, it must be discarded and a new batch mixed.

► APPLICATION

Grout all areas of the installation with the exact same procedure. The most consistent results can be achieved by filling the joints with grout until flush with surface of tile using a hard rubber float working diagonally across the grout joints to both fill and compact the joints. As soon as possible, remove all excess grout with the same rubber float. The least amount of grout left at this time on the face of the tile will make the

final clean-up easier. Most importantly, allow the grout to firm in the joint acquiring its initial set before any further cleaning is to be done. The grout is firm when it can only slightly be indented when pressed hard with your fingernail. Do not be concerned about dried grout on surface of tile at this time. Upon initial set of the grout, use a pad of cheese cloth or towel dampened with a minimum amount of clean cool water to clean tile surface by rubbing in a circular motion to further compact the grout. Also, clean off grout remaining on the surface of the tile at this time. As an alternate to the cloth pad a tool distributed by Gundloch Co. called the "Doodle Bug", a Scotch-Brite™ pad fastened to a float, works very well to remove grout from porous tiles. In no case is a sponge recommended for grouting. To help reduce efflorescence and control color variation, buff the tile surface and grout with a cheese cloth or clean, dry towel within 1 - 2 hours to remove all weep water and grout residue from the surface of the grout.

► CURING

During the first 72 hours, care must be taken to prevent the grout from drying out by covering the installation with natural kraft paper. Plastic sheeting or newspaper should not be used. Damp curing is required to maintain a moist joint on non-latex-modified grouts, it should be applied in even amounts, but in no case should standing water be allowed. During this time, it is also important to keep the installation covered with kraft paper, not plastic sheeting, to prevent staining and dirt being worked into the fresh grout joints by other construction trades.

► FINAL CLEANING

After 10 days, the floor may be re-cleaned to remove any remaining grout from the surface of the tile. Scrubbing the floor with a hot water and TSP (trisodium phosphate) method is best. It is not recommended that acids be used. If acid is required, a solution no stronger than 2 lbs. (.90 kg) of C-CLEAN 985 granules to 5 gallons (18.9 L) of water may be used. It is important that before the acid solution is placed on the surface, that the grout be thoroughly saturated with water first. Cleaning in this manner will most likely cause color alteration of the grout joint, the degree of which can be determined by doing a small test patch in an inconspicuous place.

► SEALING AND STAINING

Sealers, waxes and stains may be used to further enhance the grout by offering richer colors and future prevention of unwanted stains. A period of at least 30 days and complete satisfaction of grout conditions should be allowed before these products are applied. Some sealers may have adverse effects on grout joints, such as softening or discoloration. Try small test area to be sure.

► COVERAGE

See separate GROUTING MATERIALS COVERAGE CHART in the Specifications Section.

► WARRANTY

SUPREME 925 is included in C-Cure's Five Year System Warranty. For terms and conditions see Warranty Document #WRTDS.

Supreme 925

Dry-Set Grout

SUPREME 925 TECHNICAL DATA		
TEST		TYPICAL VALUES
A. Shear Bond ANSI A118.1		
Absorptive Tile	7 Days	>200 psi (14 kg/cm ²)
Semi-Vitreous Tile	7 Days	>300 psi (21 kg/cm ²)
B. Compressive Strength ASTM C-109		
	7 Days	>2400 psi (169 kg/cm ²)
	28 Days	>3500 psi (246 kg/cm ²)
C. Water Absorption		<12%
D. Hardness		>70 Shore D
E. Initial Set ASTM C-266		2 Hours
F. Final Set ASTM C-266		8 Hours
G. Bucket Life		6 Hours
H. Safety—CAUTION: May cause eye, skin or lung injury. Contains free silica. Prolonged exposure to dust may cause delayed lung disease (silicosis). Eliminate exposure to dust. Use NIOSH approved mask for Silica dust. Contains Portland cement. If any cement or cement mixtures get into the eye, flush immediately and repeatedly with water, and consult a physician promptly. Freshly mixed cement, mortar, concrete or grout may cause skin injury. Avoid contact with skin where possible and wash exposed skin areas promptly with water.		
KEEP OUT OF REACH OF CHILDREN.		
I. Storage Life—One year if kept dry in sealed bags.		

GUARANTEE

The recommendations, suggestions, statements and technical data are based on the best knowledge available to C-Cure and are given for informational purposes ONLY and without any responsibility for their use.

C-Cure MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT SOLD HEREIN except that the quality of the ingredients shall be in accordance with C-Cure specifications. It is expressly understood and agreed that the buyer's sole and exclusive remedy shall be replacement of defective products and under no circumstances shall C-Cure be liable for incidental or consequential damages. C-Cure neither assumes nor authorizes any others to assume for it any liability with respect to furnishing of the product. Handling and use of the product are beyond the control of C-Cure, therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from the use of the product.

This writing constitutes a complete and exclusive statement of the understanding between C-Cure and buyer. There were no oral agreements or warranties, expressed or implied, collateral to or affecting the furnishing of the product. This understanding shall not be modified except in writing by an officer of C-Cure.

Members of National Tile Contractors Association,
Materials & Methods Standards Association, Ceramic Tile Distributors Association.

NOTICE: The information in this bulletin is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent. In as much as any assistance furnished by C-Cure with reference to the safe use and disposal of its products is provided without charge, C-Cure assumes no obligation or liability therefore, except to the extent that any such assistance shall be given in good faith.

C-CURE
Seal Beach, CA 90740
800-895-2874
www.c-cure.com